

Hylon N2000STH2L NAT

Polyamide 6 Prime Compound



Product Description : Unfilled, High Impact, Polyamide 6 Compound

Key Features : HYLON N2000STH2L NAT is high heat stabilized and lubricated PA6 compound with good toughness and stiffness properties

Process Method : Injection moulding

Uses : Recommended for general applications and purposes

Revision Date : 01.12.2021

	Value	Unit	Standard
Physical			
Density	1,07	gr / cm3	ISO 1183 1-A
Mechanical			
Tensile Stress at Break	50	MPa	ISO 527-1
Elongation at Break	80	%	ISO 527-1
Tensile Modulus	1900	MPa	ISO 527-1
Izod Impact Strength (Notched) (23°C)	50	kJ/m2	ISO 180/1A
Charpy Impact Strength (Notched)	55	kJ/m2	ISO 179/1A
Izod Impact Strength (Unnotched)	NB	kJ/m2	ISO 180/1A
Izod Impact Strength (Unnotched)(-30°C)	NB	Kj/m2	ISO 180/1A
Charpy Impact Strength (Unnotched)	NB	kJ/m2	ISO 179/1U
Thermal			
HDT (0.45 Mpa)	155	°C	ISO 75B
HDT (1.8 Mpa)	55	°C	ISO 75A
Flammability			
Flammability (1,6 mm)	HB	*	UL 94
Flammability (3,2 mm)	HB	*	UL 94

Drying Condition

Drying Time(hr) 2-4



Ravago Petrokimya Uretim A.S.

Main Office : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Plant : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Mail / Web : info@ravagopetrokimya.com.tr

Tel : +90 850 314 70 99

Fax : +90 262 672 10 51

www.ravagopetrokimya.com.tr

Hylon N2000STH2L NAT

Polyamide 6 Prime Compound



Drying Temperature(°C)	90
------------------------	----

Molding Condition (°C)

1st Zone (hopper)(°C)	220-225
2nd Zone(°C)	225-230
3rd Zone(°C)	230-235
Nozzle(°C)	230-235
Mold Temperature(°C)	80

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

Ex : BM453UF0J1000
RAVAMID R200 T53 NC



Ravago Petrokimya Uretim A.S.

Main Office : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Plant : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Mail / Web : info@ravagopetrokimya.com.tr

Tel : +90 850 314 70 99

Fax : +90 262 672 10 51

www.ravagopetrokimya.com.tr